

TEST REPORT

No. :
 Date : Oct. 20,2025
 Page: 1 of 3

CUZI INDUSTRY CO., LIMITED

The following sample(s) was/ were submitted and identified on behalf of the client as:

Sample Name : FILM FACED PLYWOOD
 Sample No. :
 Material and Mark : HARD WOOD
 Date of Receipt : Sept. 27,2025
 Test Period : Sept. 27,2025 to Oct. 20,2025
 Test result(s) : For further details, please refer to the following page(s)

***** To be continued*****

Signed for SGS-CSTC Standards
 Technical Services (Shanghai) Co., Ltd

This document is issued by the Company subject to its General Conditions of Service printed overleaf, available on request or accessible at http://www.sgs.com/terms_and_conditions.htm and for electronic format documents subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of the test and is not to be used as evidence in any legal proceedings. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction or obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company, or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. The results shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days.

TEST REPORT

No. :
 Date : Oct. 20, 2025
 Page: 2 of 3

Sample Description: brown wood board

1. Bending strength and Modulus of elasticity

Sample size: 448.23mm × 456.95mm × 18.23mm (Length × Width × Thickness), 1pc

Test conducted: GB/T 17657-1999 Test methods of evaluating the properties of wood-based panels and surface decorated wood-based panels

Test result:

Test Item	Test method	Test Result
Bending strength (MPa)	GB/T 17657-1999	54.7
Modulus of elasticity (MPa)		5360

2. Surface bond strength

Test conducted: GB/T 15102-2006 Surface decorated wood-based panels with paper impregnated thermosetting resins

Test result:

Test Item	Test method	Test Requirement	Test Result	Judgement
Surface bond strength (MPa)	GB/T 15102-2006	≥0.60	1.40	Accept

3. GB 18580-2001-formaldehyde emission content

Test Method: With reference to GB/T 17657-1999 (The method of evaluating the properties of wood-based panels and surface decorated wood-based panel) clause 4.12.1~4.12.6(9-11)L, to determine the formaldehyde emission content from plywood, decorative veneered overlaid plywood and blockboard, analysis was performed by UV-Vis.

Test Item(s)	Limit	Unit	MDL	Result
Formaldehyde	1.5	mg/L	0.2	ND

Conclusion: When tested as specified, formaldehyde emission content of the submitted sample complies with the requirement of GB 18580-2001 for plywood, decorative veneered overlaid plywood and blockboard.

***** To be continued*****

TEST REPORT

No. : [REDACTED]

Date : Oct. 20, 2025

Page: 3 of 3

Sample photo:



Test Item 1-2



Test Item 3

***** End of report *****

This document is issued by the Company subject to its General Conditions of Service printed herewith, available on request or accessible at http://www.sgs.com/terms_and_conditions, for use and for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, jurisdiction and jurisdiction issues defined therein. Any holder of this document is advised that information contained herein reflects the Company's findings at the time of its inspection only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from their respective obligations under the transaction documents. This document cannot be reproduced except in full without prior written approval of the Company. Any forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law. Copies shown in this test report refer only to the sample(s) tested and such sample(s) are retained for 30 days.