

TEST REPORT

Performance test

Report Reference No. .

Tested by (name and signature) .

Approved by (name and signature) ..

Date of issue ..

January 26, 2026

Contents

Total test report 5 pages including

Report text: 3 pages

Appendix A for test data 1 page

Appendix B for product photos 1page.

Testing Laboratory name Intertek Testing Services Shenzhen Ltd.

Address ..

Testing location : Same as above

Applicant's name Cuzi Industry Co., Limited

Address

Test specification:

Standard..... BS 476-6:1989+A1 :2009

Non-standard test method... : N/A

Test item description Fire Retard Plywood

Trade Mark CUZI

Model and/or type reference 225*225*18(mm)

Manufacturer Cuzi Industry Co., Limited

Rating(s)

CONCLUSION:

Refer to test data.

Intertek **Testing** Services Shenzhen Ltd. Guangzhou Branch

Test item particulars
Classification of installation and use : —
Possible test case verdicts
- Test case does not apply to the test object..... : N/A
- Test object does meet the requirement : P (Pass)
- Test object does not meet the requirement : F (Fail)
Testing
Date of receipt of test item : January 10, 2026
Date (s) of performance of tests : January 10, 2026 to January 26, 2026
General remarks:
This report is for the exclusive use of Intertek's Client and is provided pursuant to the agreement between Intertek and its Client. Intertek's responsibility and liability are limited to the terms and conditions of the agreement. Intertek assumes no liability to any party, other than to the Client in accordance with the agreement, for any loss, expense or damage occasioned by the use of this report. Only the Client is authorized to permit copying or distribution of this report and then only in its entirety. Any use of the Intertek name or one of its marks for the sale or advertisement of the tested material, product or service must first be approved in writing by Intertek. The observations and test results in this report are relevant only to the sample tested. This report by itself does not imply that the material, product, or service is or has ever been under an Intertek certification program. "(see remark #)" refers to a remark appended to the report. "(see Appendix #)" refers to an appendix appended to the report. Throughout this report a comma (point) is used as the decimal separator. When determining the test result, measurement uncertainty has been considered.
General product information:
The test sample named Fire Retard Board, Submitted sample dimension: 225×225×18mm. Refer to 'Appendix B Product Photo' for details.

BS 476-6			
Clause	Requirement - Test	Result - Remark	Verdict
↓	Fire propagation Prior to testing, the sample was conditioned, to constant mass at a temperature of 23 ± 2 °C, and a relative humidity of 50 ± 10 %, and maintained in this condition until required for testing. Three specimens with dimension of 225×225mm were tested according to clause 9 of BS 476-6, and the test result was calculated through clause 10 of BS 476-6.	Fire propagation index: 18.87; Refer to 'Appendix A – Test data' for detail.	↓

*****End of Page*****

Appendix A

Test Data

Throughout the test on each specimen, carefully observe the material's behaviour within the apparatus and take special note of any of the following phenomena listed in clause 9.2 of the standard. None of the listed phenomena was observed and the test results on all three specimens tested were valid.

The index of the performance for the specimen was determined as follows:

$$S_1 = \sum_{t=0.5}^{t=3} \frac{\theta_s - \theta_c}{10t}, S_2 = \sum_{t=4}^{t=10} \frac{\theta_s - \theta_c}{10t}, S_3 = \sum_{t=12}^{t=20} \frac{\theta_s - \theta_c}{10t}, S = S_1 + S_2 + S_3$$

Where:

S = index of performance for each of the specimens tested and S1, S2 and S3 are sub-indices;

t = Time in minutes from the origin which reading are taken;

θ_s = Temperature rise in °C for the specimen at time, t;

θ_c = Temperature rise in °C for the calibration sheet at time, t.

Fire Propagation index $I = i_1 + i_2 + i_3$

Where, i_1 , i_2 and i_3 are given by the expressions:

$$i_1 = \frac{1}{3} [(S_1)_A + (S_1)_B + (S_1)_C], i_2 = \frac{1}{3} [(S_2)_A + (S_2)_B + (S_2)_C], i_3 = \frac{1}{3} [(S_3)_A + (S_3)_B + (S_3)_C]$$

The following test results were obtained for each specimen tested:

Specimen No.	Sub-indices			Index of performance
	S1	S2	S3	S
A	5.35	8.09	5.65	19.09
B	5.08	7.99	5.63	18.69
C	5.25	7.99	5.61	18.85
Number of specimens tested	Sub-index	Sub-index	Sub-index	Fire propagation
	i_1	i_2	i_3	I
3	5.22	8.02	8.63	18.87

Note: If a suffix "R" is included in the above fire propagation index I, this indicates that the results should be treated with caution.

*****End of Page*****

Appendix B

Product photo



*****End of Report*****